



PRODUCT DATA SHEET

weberbase easi render

Semi-coarse and water-resistant sprayable pre-mixed plaster for interior and exterior use

PRODUCT

weberbase easi render is a high-quality water-resistant sprayable cement-based plaster for application on brick walls, block walls, panel walls and concrete surfaces.

weberbase easi render is suitable for dry and wet interiors as well as exteriors and serves as a render coat underneath **weber Tile Adhesive & Tile Grout** series for tile fixing. To achieve a finer surface finishing, **weberbase easi render** may be overcoated with **weber Skim Coat** series before painting. This product shall not be used on painted surfaces.

Uses

- Interior wall rendering
- Exterior wall rendering
- Panel wall rendering
- Small area ceiling rendering (with **webertec bond coat** or **webertec eva**)

Features and Benefits

- Formulated to comply with European Norm, British Standard and Chinese Standard
- Single component: fixed mixing proportion, ensure the quality of work
- Specific design for spray plastering
- Shrinkage compensated: reduces the chance of shrinkage cracks
- Suitable for tiling with **weber Tile Adhesive & Tile Grout** series products
- After receiving **weber Skim Coat** series, a finer surface profile is available for painting
- Compatible with cementitious waterproofing materials **weber Waterproofing** series products

TECHNICAL DATA

Colour	Grey
Component	Portland cement, non-reactive aggregate, graded sand and other chemical additives
Max. aggregate size	2.0 mm
Water demand	Hand application: Approx. 16 – 18% (6.4 – 7.2 L/40 KG bag) Spray application: Approx. 17 – 19% (6.8 – 7.6 L/40 KG bag)
Density	1.6 kg/L (dry) 1.8 kg/L (wet) for 16% water demand
Pot life	Approx. 1 hour
Thickness	8 – 15 mm for 1 coat 15 – 25 mm for 2 coats 25 – 35 mm for 3 coats
Coverage	Approx. 1.55 kg/m ² /mm
Theoretical consumption	Approx. 15.5 kg/m ² for a thickness of 10 mm Approx. 2.5 m ² /40 kg bag for a thickness of 10 mm

Saint-Gobain Hong Kong, Macau, Taiwan

Saint-Gobain Hong Kong Limited

Room 1601-8, 16/F, Tai Yau Building, 181 Johnston Road, Wan Chai, Hong Kong

T: (+852) 2866 9199 F: (+852) 2865 0321

info.hk@saint-gobain.com www.saint-gobain.hk



PHYSICAL PROPERTIES

Test characteristics	Test methods	Results
Density	BS EN 1015 – 10	1840 kg/m ³
Tensile adhesion strength	BS EN 1015 – 12	≥ 2.0 N/mm ²
Tensile adhesion strength (saw-cut method)	BS EN 1015 – 12	≥ 1.5 N/mm ²
Flexural strength	BS EN 1015 – 11	≥ 4.0 N/mm ²
Compressive strength	BS EN 1015 – 11	≥ 15 N/mm ²
Chloride content	BS1881: Part 124	< 0.01%
Shrinkage	Coutinho Ring HKHA MTS Spec. Part D, Cl. 2.1.6	No cracks observed

Unless specified, all technical data are average values and refer to 28-day curing time.

The above physical data are taken from laboratory tests. In situ material performance may vary according to environmental & workmanship conditions beyond the manufacturer's control.

Complied Standards

European Norm : BS EN 1015 – 10, 11, 12
British Standard : BS 1881: Part 124

PROCEDURE

Substrate Preparations

Substrate must be free from grease, mould oil, rust, rusty metal, wood peels, paints, plastics, loose particles, contamination on any traces of foreign materials affecting the adhesion of **weberbase easi render**.

Moisten the substrate the night before and also at the time before the commencement of operation. Neither stagnant water nor continuous water flow on the substrate is allowed immediately prior to plastering.

When the substrate is concrete with high fly ash content, the surface should be sealed with **weberprim moisture sealer** beforehand.

Mixing and Installation

Mix a bag of dry-mixed powder (40 KG) with an appropriate amount of water (depending on the application mode) by using an electrical mixer for 3 – 7 minutes. For hand application, add approx. 16 – 18% (6.4 – 7.2 L) of water; for spray application, add approx. 17 – 19% (6.8 – 7.6 L) of water.

Apply the render by hand or spraying machine to the required thickness in layer(s). For clean, smooth and flat concrete surfaces, **weberbase easi render** in a thin application can be applied directly on the concrete surface without spatterdash. For thick application on concrete substrates, a coat of sound spatterdash shall be applied in order to provide a good key for receiving **weberbase easi render**.

Please refer to our method statement for procedures in detail.

Curing

Water mist is preferred but not always necessary for interior applications. However, water mist is required under extreme hot or dry weather conditions.

STORAGE AND PACKING

weberbase easi render is delivered in a 40 kg bag. Storage life is 12 months if the product is kept in a dry place.

HEALTH AND SAFETY

Recommend wearing a NIOSH-approved or equivalent particulate face mask when mixing the material.

The material contains cement, which may produce an allergic reaction.

Keep out of reach of children.

Material may cause irritation to the eyes and skin. In case of contact with the eyes, rinse immediately with plenty of water and seek medical assistance. After contact with skin, wash immediately with plenty of soap and water.

Please refer to the Material Safety Data Sheet (MSDS) for health, safety and handling of the product.

CLEANING & DISPOSAL OF WASTE

Cured material can be removed mechanically; if uncured, material can be removed with water. Dispose of waste in accordance with legislation.

* Note: The information and physical data in this catalogue are given to the best of our knowledge under standard testing methods and a controlled environment. The results may vary with different weather/site conditions, workmanship or substrates. This is beyond our control, and we shall not be liable for any faults or consequences arising from or associated with this. We suggest that comprehensive tests be conducted before the final application. Unless specified, all technical data are average values with a curing time of 28 days. We reserve the right to update or amend the contents in the light of new findings during the course of research and development.